



## GENERAL INFORMATION

PR1 Plastic Cleaner removes mold release agents and other surface contaminant's from plastics. PR1 must be used prior to application of PR2.



### 1. APPLICATION

- Spray surface with PR1 and wipe dry with clean cloth before product evaporates.
- Scuff surface with 400 grit wet or dry sandpaper or gray/yellow scuff pad.
- Re-spray surface with PR1 and wipe dry with clean cloth before product evaporates.
- Use PR2 Plastic Adhesion Promoter as required. (See PR2 Data Sheet)



### 2. SUBSTRATES

- Commonly used automotive interior and exterior plastics
- TPO -Thermopolyolefin
- RIM- Reaction Injected Molded Polyurethane
- PVC - Polyvinyl Chloride
- PPO - Polypropylene



### 3. PHYSICAL DATA

VOC 0.17 lbs./gal.

## NOTES