

AB300 Aerosol Blending Solvent



GENERAL INFORMATION

AB300, fast and efficient method for blending newly applied clear coats or 2K topcoats into existing cured finish.



1. COMPONENTS

AB300 Blending Solvent



2. MIXING RATIO

· Ready to use

For USA/Canada compliant rules:

· Regulated as Aerosol Coating, ready for use



POT LIFE @ 77°F (25°C)

Indefinite



4. CLEAN UP

• To clean nozzle: Invert can and spray for about three (3) seconds.



5. ADDITIVES

N/A



6. SURFACE PREPARATION

· Surface blend area should be clean and free of any defects



7. TOPCOATS

N/A



8. TECH NOTES

 The blending of clear coats and 2K topcoats is often required for Smart Repair and other repair conditions; however Valspar does not warranty this process



9. SUBSTRATES

- · Clear Coats
- · 2K Topcoats



10. APPLICATION

- Shake can for 30 seconds per initial daily use, after shake for 10 seconds prior to each use.
- · Allow final layer of clear coat or 2K topcoat to flash for 30-60 seconds
- Apply first mist coat of AB300 to the blend edge of the clear coat or 2K topcoat, allow AB300 10–15 seconds to dissolve the edge, evaluate the finish and if needed apply a second coat of AB300



11. FLASH / DRY TIMES

• N/A



12. INFRARED CURE

N/A



13. GUN SET UP

N/A



14. PHYSICAL DATA

FOR USA/Canada (US Regulated - Aerosol Coatings)

	AB300	
RTS REGULATORY DATA:	Ready for Use	
	LBS./GAL	g/L
Actual VOC	5.9 Max	705 Max
Density	5.5 - 6.5	660 - 780
	WT.%	VOL.%
Total Solids Content	0.3 - 1.0	0.2 - 1.0
Total Volatile Content	99.0 - 99.7	99.0 - 99.8
Water	0	0
Exempt Compound Content	0	0
Coating Category	Uniform Finish Coating (CA) / CCP (Federal)	
Product Weighted Reactivity	1.3 Max (CA) / 1.5 Max (Federal)	

NOTE: US Regulations allow for the use of exempt compounds for VOC calculations

FOR REST-OF-WORLD (outside US and Canada):

	AB300	
RTS REGULATORY DATA:	Ready for Use	
	LBS./GAL	g/L
VOC	7.0 Max	840 Max
Density	5.5 - 6.5	660 - 780
	WT%	VOL%
Total Solids Content	0.3 - 1.0	0.2 - 1.0
Total Volatile Content	99.0 - 99.7	99.0 - 99.8
Water	0	0
Coating Category	Specialty Coating	

NOTES

If used as instructed, this product is designed to comply with US Aerosol Coating and California Air Resources Board Aerosol Coating Product Regulations. Confirm compliance with state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information. UNLESS VALSPAR AGREES OTHERWISE IN WRITING, VALSPAR MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. VALSPAR WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.